

## PRODUCT DATA SHEET

# SikaCeram® CleanGrout

#### CEMENTITIOUS FLOOR/WALL TILE GROUT FOR JOINTS 1-8 MM

#### **DESCRIPTION**

SikaCeram® CleanGrout is a cementitious setting, floor /wall tile grout powder for use in joints from 1–8 mm in width. Additives contained in the powder provide protection against mould, bacterial and fungal growth while maintaining a colour stable, abrasion resistant, water repellent durable finish. For indoor and outdoor use.

#### **USES**

#### Grouting the following tile types:

- Ceramic
- Earthenware
- Glass mosaic
- Marble and other natural stones
- Grès porcelain

## Grouting tiles for the following high performance and demanding applications:

- Swimming pools
- Heated floors
- Commercial / Industrial / Residential environments
- Facades

### **CHARACTERISTICS / ADVANTAGES**

- Floor and wall application
- Water-repellent
- Abrasion resistant
- High degree of hardness
- UV resistant
- Frost proof
- Contains mould protection


### PRODUCT INFORMATION

Chemical Base	Polymer modified, portland cement based, with selected fine silica/quartz sand, water retainers and other special additives.					
Packaging	5 kg and 2 kg bags. Refer to current price list for packaging variations.					
Appearance / Colour	Colours:					
	White	Light Grey	Silver	Manhattan	Ice	
	Grey	Ash	Anthracite	Graphite	Total black	
	Pergamon	Jasmine	Anemone	Beige	Pine	
	Caramel	Maple wood	Dove Grey	Light Sand	Sand	
	Cedar	Beech wood	Walnut	Oak wood	Brown	
	Terracotta	Amaranth	Ruby	Dark Brown	Mahogany	
Shelf Life	24 months from date of production.					

Product Data Sheet SikaCeram® CleanGrout April 2020, Version 03.01 021720100000000017

Storage Conditions	packaging in c	Product must be stored in original, unopened and undamaged sealed packaging in dry conditions at temperatures between +5 °C and +30 °C. Always refer to packaging.				
Maximum Grain Size	D <sub>max</sub> : 0,25 mm	D <sub>max</sub> : 0,25 mm				
Product Declaration	CG2WA	CG2WA (EN 1388				
Water Absorption	After 30 min		≤1 g		(EN 12808-5)	
	After 240 min		≤3 g		<u> </u>	
TECHNICAL INFORMATION	ON					
Abrasion Resistance	≤ 1000 mm³			(EN 12808-2)		
Compressive Strength	After dry storage After freeze/thaw cycles		≥ 20 N/mm <sup>2</sup> ≥ 15 N/mm <sup>2</sup>		(EN 12808-3)	
Tensile Strength in Flexure	After dry storage		≥ 4 N/mm²		(EN 12808-3)	
		After freeze/thaw cycles		≥ 3 N/mm²		
Shrinkage	≤ 3 mm/m	≤ 3 mm/m			(EN 12808-4)	
Microbiological Resistance	Bacteria survival		0 %		(Protocol CCB - RP	
	Colonization		No growth		335/10/S)	
Joint width	1–8 mm					
APPLICATION INFORMA	TION					
Mixing Ratio	5 kg bag ~1,3 litres of water (26.5			% ± 1 %)		
	2 kg bag ~0,5 litres of water (26 %					
	2 kg bag		~0,5 litres of wa	ater (26 9	% ± 1 %)	
Fresh Mortar Density	2 kg bag ~2,05 kg/l		°0,5 litres of wa	ater <u>(26</u> 9	% ± 1 %)	
Fresh Mortar Density  Consumption	~2,05 kg/l The consumpt depth. As a guide, con g/m².	ion is deper	ndent on the sizes indicated in fo	ze of the tiles, j	oint width and	
·	~2,05 kg/l The consumpt depth. As a guide, co	ion is deper	ndent on the sizes indicated in fo	ze of the tiles, j	oint width and	
·	~2,05 kg/l  The consumpt depth. As a guide, cong/m².  Tile Size  Centimetres  Glass mosaic	ion is deper nsumption i	ndent on the sizes indicated in fo	ze of the tiles, j	oint width and and is expressed in	
·	~2,05 kg/l  The consumpt depth.  As a guide, cong/m².  Tile Size  Centimetres	ion is deper nsumption is Joint Widtl 2 mm	ndent on the sizes indicated in fo	ze of the tiles, j	oint width and and is expressed in	
	~2,05 kg/l  The consumpt depth. As a guide, cong/m².  Tile Size  Centimetres  Glass mosaic 2 × 2 × 0,4	ion is depernsumption is  Joint Widtl 2 mm  1300	ndent on the sizes indicated in fo	ze of the tiles, j	oint width and and and is expressed in	
	~2,05 kg/l  The consumpt depth. As a guide, cong/m².  Tile Size  Centimetres  Glass mosaic $2 \times 2 \times 0,4$ $5 \times 5 \times 0,4$ $10 \times 10 \times 0,6$ $15 \times 15 \times 0,9$	Joint Widtl 2 mm 1300 450 350	andent on the sizes indicated in form  3 mm  500 500	ze of the tiles, jollowing table at the second seco	oint width and and is expressed in 8 mm - 1350 1350	
	~2,05 kg/l  The consumpt depth.  As a guide, cong/m².  Tile Size  Centimetres  Glass mosaic $2 \times 2 \times 0,4$ $5 \times 5 \times 0,4$ $10 \times 10 \times 0,6$ $15 \times 15 \times 0,9$ $20 \times 20 \times 0,9$	Joint Widtl 2 mm 1300 450 350 350 250	3 mm - 500 500 380	ze of the tiles, jollowing table and selection in the sel	8 mm - 1350 1350 1000	
	~2,05 kg/l  The consumpt depth.  As a guide, cong/m².  Tile Size  Centimetres  Glass mosaic $2 \times 2 \times 0,4$ $5 \times 5 \times 0,4$ $10 \times 10 \times 0,6$ $15 \times 15 \times 0,9$ $20 \times 20 \times 0,9$ $30 \times 30 \times 1$	Joint Widtl 2 mm 1300 450 350 350 250	3 mm - 500 500 380 280	5 mm - 840 840 630 470	8 mm - 1350 1350 1000 750	
	~2,05 kg/l  The consumpt depth. As a guide, cong/m².  Tile Size  Centimetres  Glass mosaic $2 \times 2 \times 0,4$ $5 \times 5 \times 0,4$ $10 \times 10 \times 0,6$ $15 \times 15 \times 0,9$ $20 \times 20 \times 0,9$ $30 \times 30 \times 1$ $30 \times 60 \times 1$	Joint Widtl 2 mm 1300  450 350 350 250 190 140	3 mm - 500 500 380 280 210	5 mm -  840 840 630 470 350	8 mm - 1350 1350 1000 750 560	
·	~2,05 kg/l  The consumpt depth. As a guide, cong/m².  Tile Size  Centimetres  Glass mosaic $2 \times 2 \times 0,4$ $5 \times 5 \times 0,4$ $10 \times 10 \times 0,6$ $15 \times 15 \times 0,9$ $20 \times 20 \times 0,9$ $30 \times 30 \times 1$ $30 \times 60 \times 1$ $50 \times 50 \times 1$	Joint Widtl 2 mm 1300 450 350 350 250 190 140	s indicated in form  3 mm  -  500  500  380  280  210  170	5 mm - 840 840 630 470 350 280	8 mm - 1350 1350 1000 750 560 450	
·	~2,05 kg/l  The consumpt depth. As a guide, cong/m².  Tile Size  Centimetres  Glass mosaic $2 \times 2 \times 0,4$ $5 \times 5 \times 0,4$ $10 \times 10 \times 0,6$ $15 \times 15 \times 0,9$ $20 \times 20 \times 0,9$ $30 \times 30 \times 1$ $30 \times 60 \times 1$	Joint Widtl 2 mm 1300 450 350 350 250 190 140	3 mm - 500 500 380 280 210	5 mm -  840 840 630 470 350	8 mm - 1350 1350 1000 750 560	
·	~2,05 kg/l  The consumpt depth.  As a guide, cong/m².  Tile Size  Centimetres  Glass mosaic $2 \times 2 \times 0,4$ $5 \times 5 \times 0,4$ $10 \times 10 \times 0,6$ $15 \times 15 \times 0,9$ $20 \times 20 \times 0,9$ $30 \times 30 \times 1$ $30 \times 60 \times 1$ $50 \times 50 \times 1$ $60 \times 120 \times 1,1$ These figures	Joint Widtl 2 mm 1300 450 350 250 190 140 110 80 are theoreti	s indicated in form  3 mm  500  500  380  280  210  170  110  cal and do not	5 mm -  840 840 630 470 350 280 200 allow for any a	8 mm - 1350 1350 1000 750 560 450	
·	~2,05 kg/l  The consumpt depth. As a guide, cong/m².  Tile Size  Centimetres  Glass mosaic $2 \times 2 \times 0,4$ $5 \times 5 \times 0,4$ $10 \times 10 \times 0,6$ $15 \times 15 \times 0,9$ $20 \times 20 \times 0,9$ $30 \times 30 \times 1$ $30 \times 60 \times 1$ $50 \times 50 \times 1$ $60 \times 120 \times 1,1$ These figures due to surface	Joint Widtl 2 mm 1300  450 350 250 190 140 110 80 are theoretic porosity, so (g/m²) = A × (mm)	s indicated in form  3 mm  -  500  500  380  280  210  170  110  cal and do not urface profile, where the control of the contr	5 mm -  840 840 630 470 350 280 200 allow for any avariations in level of the following stable at the	oint width and and is expressed in  8 mm -  1350 1350 1000 750 560 450 310 dditional material rel or wastage etc. formula:	
·	~2,05 kg/l  The consumpt depth.  As a guide, cong/m².  Tile Size  Centimetres  Glass mosaic $2 \times 2 \times 0,4$ $5 \times 5 \times 0,4$ $10 \times 10 \times 0,6$ $15 \times 15 \times 0,9$ $20 \times 20 \times 0,9$ $30 \times 30 \times 1$ $30 \times 60 \times 1$ $50 \times 50 \times 1$ $60 \times 120 \times 1,1$ These figures due to surface  Consumption Consumption A = Gap width	Joint Widtl 2 mm 1300  450 350 250 190 140 110 80  are theoretic porosity, so (g/m²) = A × (mm) (mm)	s indicated in form  3 mm  -  500  500  380  280  210  170  110  cal and do not urface profile, where the control of the contr	5 mm -  840 840 630 470 350 280 200 allow for any a variations in level the following x D)] × 140.	oint width and and is expressed in  8 mm -  1350 1350 1000 750 560 450 310 dditional material rel or wastage etc. formula:	

+5 °C min. / +35 °C max.



**Substrate Temperature** 



Waiting Time	Before grouting on floor tiles laid with:	Waiting time			
	Normal-setting adhesive	24–36 hours 4–6 hours			
	Fast-setting adhesive				
	Thick-bed (traditional) adhesive	8–10 days			
	Before grouting on wall tiles laid with:				
	Normal-setting adhesive	4–6 hours 2 hours			
	Fast-setting adhesive				
	Above times are indicative. Always consult the appropriate tile adhesive Product Data Sheet.				
Applied Product Ready for Use	Use	Waiting time			
	Walkability	24–36 hours			
	Full traffic	~14 days			
	Water immersion	~21 days			

#### **APPLICATION INSTRUCTIONS**

#### SUBSTRATE QUALITY / PRE-TREATMENT

Check joints are dry, clean, and clear of excess adhesive, contaminants and tile joint spacers. Remove from joint before grout application.

For applications in hot climates / environments, or on absorbent substrates, thoroughly pre-dampen the surface immediately prior to product application. Avoid any ponding / standing water on the surface. Surface must not be damp to touch.

#### **MIXING**

Pour the recommended amount of clean cold water into a suitable, clean mixing container.

Slowly add SikaCeram® CleanGrout powder to the water while mixing using a low speed (~500 rpm) drill mixer. Then mix thoroughly until the material is fully mixed and lump free. Avoid entraining air into the mix by over mixing.

Allow the product to stand for 2–3 minutes before remixing for 30 seconds.

The finished mix has a creamy consistency, uniformly coloured and is easy to apply and spread.

For areas requiring only small quantities, these can be mixed by hand. Measure the water: powder ratio carefully as small differences in the mix ratio can result in colour shade variations.

For high-performance and demanding applications, such as heavily-trafficked floors, exposed facades, swimming pools or for additional flexibility, the water can be replaced with a solution of SikaCeram® Latex-Grout (Refer to the individual Product Data Sheet)

#### **APPLICATION**

Before grouting check adhesive has fully set. SikaCeram® CleanGrout is applied using an appropriate tool such as a grout spreader, squeegee or grouting float/trowel.

Completely fill and compact the joints uniformly. If required, finish grout with a grout finishing tool

while grout is wet.

Using the same spreader/ float, remove excess grout from the tile surfaces moving the tool diagonally across the joints.

When the grout is touch dry. Use a damp sponge or sponge float to clean the tile surfaces. Clean sponge regularly with clean water.

When grout has set hard enough in the joint (finger nail hard). Polish the tile surfaces by wiping with a clean, soft dry cloth.

If SikaCeram® LatexGrout has been used instead of water in the grout mix, polish the tile surfaces immediately after the initial cleaning with a damp sponge.

#### **CLEANING OF TOOLS**

Clean all tools and application equipment with water after use. Hardened material can only be removed mechanically

#### **LIMITATIONS**

- Do not exceed the recommended amount of water in the mix. The mix must never be fluid.
- Do not add or allow any additional water to be added into the mixed product during or after mixing.
- Prevent contact of freshly applied material with water (including rain), except during cleaning operations. Also prevent exposure with excess atmospheric humidity / condensation or residual moisture in the substrate etc.
- Avoid significant temperature variation during application and setting times, as well as excessive draughts, forced ventilation or winds.
- Excess water and ventilation, temperature variations, application on very porous tiles or on substrates leading to rapid water absorption etc. can result in colour shade variations.
- When coloured grout is applied for aesthetics such as on polished porcelain or natural stone tiles, always carry out cleanability testing on a small area prior to full application.
- On highly absorbent tiles, it is always recommended to thoroughly pre-dampen the surface before grout-



ing.

- Always apply SikaCeram® CleanGrout in a continuous operation and do not interrupt for more than two hours in the same room or area of tiling.
- Premature exposure to water or excess water in the mix can result in white efflorescence on the grout surface.
- Avoid application in direct sunlight to avoid cracking in the joint.
- Ensure grout has set sufficiently before carrying out the tile cleaning procedure to avoid grout being removed from joint.
- Do not add anything to the product that is not specified in this Product Data Sheet.
- Do not use for any applications not explicitly described in this Product Data Sheet.

#### **BASIS OF PRODUCT DATA**

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

#### LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the declared data for this product may vary from country to country. Please consult the local Product Data Sheet for the exact product data.

#### **ECOLOGY**

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet (SDS) containing physical, ecological, toxicological and other safety-related data.

#### **LEGAL NOTES**

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

Sika Taiwan Ltd.

No. 1380, Sec. 3, Fu-Kwo Rd., Luchu Dist. 338009 Taoyuan City, Taiwan, R.O.C. TEL: 03 352 8622 . FAX: 03 352 0470 sika@tw.sika.com . twn.sika.com

SikaCeramCleanGrout-en-TW-(04-2020)-3-1.pdf

