

Product Data Sheet
Edition 29/08/2011
Identification no:
02 06 06 01 001 0 000001
Sikagard®-62

Sikagard®-62

2-Part Epoxy Protective coating

Product Description

Sikagard®-62 is a 2-pack solvent-free high build coating material based on epoxy resin.

Uses

- As an abrasion-resistant universal coating material designed for normal to moderately aggressive chemical environments. Sikagard®-62 is suitable for use on concrete, stone, cementitious mortars and renderings (not polymer-modified), epoxy cements (EpoCem), epoxy mortars, iron and steel.
- For linings in storage tanks and silos, bund areas. As anti-corrosion coating in food-processing plants, sewage works, farms and agricultural enterprises, chemical and pharmaceutical plants, beverage industries and bottling plants.
-

Characteristics / Advantages

- Solvent-free
- Good chemical and mechanical resistance
- Easy to mix and work
- High-build
- Impervious to liquids

Product Data

Form

Appearance / Colours

Resin - Part A: Coloured, liquid
Hardener - Part B: Transparent, liquid

Pebble grey (RAL 7032). Additional colour shades on request.

Under sun radiation it may come to discolouration and colour deviation; this has no influence to the function of the coating.

Packaging

Part A: 3.75 kg containers
Part B: 1.25 kg, containers
Part A+B: 5.0 kg ready to mix units

Storage

Storage Conditions/ Shelf-Life

12 months from date of production if stored properly in undamaged sealed containers in dry conditions at temperatures between +5°C and +30°C.

Technical Data

Chemical Base

Epoxy resin

Construction



Density	Part A: ~ 1.45 kg/litre Part B: ~ 1.02 kg/litre Mixed resin: ~ 1.37 kg/litre All density values at +23 °C													
Solid Content	~ 100% (by volume), ~ 100% (by weight)													
Mechanical / Physical Properties														
Bond Strength	> 1.5 N/mm ² (failure in concrete)	ISO 4624												
Resistance														
Chemical Resistance	See separate chemical resistance list													
Thermal Resistance	<table border="1"> <tr> <td>Exposure*</td> <td>Dry heat</td> </tr> <tr> <td>Permanent</td> <td>+50 °C</td> </tr> <tr> <td>Short-term max. 7 d</td> <td>+80 °C</td> </tr> <tr> <td>Short-term max. 12 h</td> <td>+100 °C</td> </tr> </table> <p>Short-term humid heat* up to +80 °C where exposure is only occasional (steam cleaning etc.).</p> <p>*No simultaneous chemical load.</p>		Exposure*	Dry heat	Permanent	+50 °C	Short-term max. 7 d	+80 °C	Short-term max. 12 h	+100 °C				
Exposure*	Dry heat													
Permanent	+50 °C													
Short-term max. 7 d	+80 °C													
Short-term max. 12 h	+100 °C													
System Information														
System Structure	<i>Roller coating:</i> Primer: 1 x Sikagard®-62 Coating: 2 - 3 x Sikagard®-62													
Application Details														
Consumption / Dosage	<table border="1"> <thead> <tr> <th>Coating System</th> <th>Product</th> <th>Consumption</th> </tr> </thead> <tbody> <tr> <td colspan="3"><i>Roller coating</i></td> </tr> <tr> <td>Priming</td> <td>Sikagard®-62</td> <td>0.3 - 0.5 kg/m²</td> </tr> <tr> <td>Roller coating</td> <td>Sikagard®-62</td> <td>0.4 - 1.0 kg/m² per coat, depending on substrate condition and coating thickness required</td> </tr> </tbody> </table> <p>For a theoretical dry film thickness of 100 microns (0.1 mm) approx. 0.14 kg/m². These figures are theoretical and do not include for any additional material required due to surface porosity, surface profile, variations in level or wastage etc.</p>		Coating System	Product	Consumption	<i>Roller coating</i>			Priming	Sikagard®-62	0.3 - 0.5 kg/m ²	Roller coating	Sikagard®-62	0.4 - 1.0 kg/m ² per coat, depending on substrate condition and coating thickness required
Coating System	Product	Consumption												
<i>Roller coating</i>														
Priming	Sikagard®-62	0.3 - 0.5 kg/m ²												
Roller coating	Sikagard®-62	0.4 - 1.0 kg/m ² per coat, depending on substrate condition and coating thickness required												
Substrate Quality	<p>The concrete substrate must be sound and of sufficient compressive strength (minimum 25 N/mm²) with a minimum pull off strength of 1.5 N/mm².</p> <p>The substrate must be clean, dry and free of all contaminants such as dirt, oil, grease, coatings and surface treatments, etc.</p> <p>If in doubt apply a test area first.</p>													
Substrate Preparation	<p>Concrete substrates must be prepared mechanically using abrasive blast cleaning or scarifying equipment to remove cement laitance and achieve an open textured surface.</p> <p>Weak concrete must be removed and surface defects such as blowholes and voids must be fully exposed.</p> <p>Repairs to the substrate, filling of blowholes/voids and surface levelling must be carried out using appropriate products from the Sikafloor®, SikaDur® and Sikagard® range of materials.</p> <p>The concrete or screed substrate has to be primed or levelled in order to achieve</p>													

an even surface.

High spots must be removed by e.g. grinding.

All dust, loose and friable material must be completely removed from all surfaces before application of the product, preferably by brush and/or vacuum.

Steel and iron surfaces must be sandblasted (SA 2 ½).

Application Conditions / Limitations

Substrate Temperature +8°C min, +30 °C max

Ambient Temperature +8C min, +30 °C max

Substrate Moisture Content ≤ 4% moisture content. Test method: Sika®-Tramex or CM.
No rising moisture according to ASTM (Polyethylene-sheet).

Relative Air Humidity 80% r.h. max

Dew Point Beware of condensation!

The substrate and uncured floor must be at least 3°C above the dew point to reduce the risk of condensation or blooming on the floor finish.

Application Instructions

Mixing Ratio / Dosage Part A : Part B = 75 : 25 (by weight)

Mixing Time Prior to mixing stir Part A mechanically. When all of Part B has been added to Part A continuously mix for 3 minutes until a uniform mix has been achieved.
To ensure thorough mixing pour materials into another container and mix again to achieve a consistent mix.
Over mixing must be avoided to reduce air entrainment.

Mixing Tools Sikagard®-62 must be mechanically mixed using an electric power stirrer (300 - 400 rpm) or other suitable equipment.

Application Method / Tools Prior to application, confirm substrate moisture content, r.h and dew point.
Coating:
Sikagard®-62 , can be applied with a distemper brush, a short-piled, solvent resistant, non-fuzzy roller or by airless spray equipment

Cleaning of Tools Clean all tools and application equipment with Thinner C immediately after use. Hardened/cured material can only be mechanically removed.

Potlife Max. open times

Temperatures	Time
+10°C	~ 30 mins
+20°C	~ 20 mins
+30°C	~ 10 mins

**Waiting Time /
Overcoatability**

Before applying Sikagard®-62 on Sikagard®-62 allow:

Substrate Temperature	minimum	maximum
+10 °C	30 hours	3 days
+20 °C	10 hours	2 days
+30 °C	6 hours	1 days

Times are approximate and will be affected by changing ambient conditions.

**Notes on Application /
Limitations**

Do not apply Sikagard®-62 on substrates in which significant vapour pressure may occur.

If > 4% moisture content, Sikafloor® EpoCem® may be applied as a T.M.B. (temporary moisture barrier) system.

Stability in vertical surface: < 300 µm (wet film thickness)

Freshly applied Sikagard®-62 must be protected from damp, condensation and water for at least 24 hours.

Avoid puddles on surface.

The incorrect assessment and treatment of cracks may lead to a reduced service life and reflective cracking.

For exact colour matching, ensure Sikagard®-62 is applied from the same control batch numbers.

Curing Details**Applied Product ready
for use**

Temperature	Foot Traffic	Light Traffic	Full cure
+ 10 °C	~ 2 days	~ 5 days	~ 14 days
+ 20 °C	~ 1 days	~ 4 days	~ 10 days
+ 30 °C	~ 18 hours	~ 2 days	~ 5 days

Times are approximate and will be affected by changing ambient conditions.

Value Base All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

Local Restrictions Please note that as a result of specific local regulations the performance of this product may vary from country to country. Please consult the local Product Data Sheet for the exact description of the application fields.

Health and Safety Information For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Material Safety Data Sheet containing physical, ecological, toxicological and other safety-related data.

Legal Notes The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.



台灣西卡股份有限公司
33849 桃園縣蘆竹鄉富國路三段 1380 號
TEL :03-352-8622 FAX: 03-352-0470
sika@tw.sika.com / www.sika.com.tw

Sika Services AG
Tüffenwies 16
CH-8048 Zurich
Switzerland

Phone +41 44 436 40 40
Telefax +41 44 436 46 86
www.sika.com

