

PRODUCT DATA SHEET

SikaGrout®-9500

Ultra-high strength, high modulus, cement based grout with applied nanotechnology for grouting offshore wind turbine installations

DESCRIPTION

SikaGrout®-9500 is a shrinkage compensated, cement based grout which when mixed with water, produces a homogeneous, flowable and pumpable grout with exceptionally high early and final strength and modulus. Latest best binder packing models and applied cementitious nanotechnology produces a grout with superior technical performance, exceptional rheological properties, and, uniquely, extended open times.

USES

SikaGrout®-9500 has been especially formulated for large scale, pump applications.

- Grouting of wind turbine installations, e.g. foundations, monopiles, transition pieces of wind towers, where very good fatigue resistance is required.
- Grouting under very harsh conditions, e.g. offshore applications or below water grouting, at temperatures as low as 0°C.
- All void filling from 25mm to 600mm thickness where high strength, high modulus is important (in other applications or where void dimensions of 10 - 25 mm are to be filled contact our technical department).

Contact the Technical Department of your local Sika office regarding any application required not mentioned here.

CHARACTERISTICS / ADVANTAGES

- Certified by Det Norske Veritas (DNV)
- Ultra-high mean compressive strength ≥ 135 MPa.
- Ultra-high modulus for exceptional stiffening properties.
- Very good fatigue resistance.
- Quick return to service and removal of temporary supports due to high early strength build-up. ≥ 60 MPa at 24hours under 20°C

- Excellent strength gain at low temperatures at 24 hours under 0°C
- No segregation or bleeding to ensure consistent final physical performance and to prevent pump block-ages
- No wash-out during below water grouting
- Pump able over long distances and large heights.
- Extended pot life of ≥ 4 hours
- Specially graded sands and exceptional flow and low friction increases pump output, reduces installation times and costs as well as reducing pump pressures and wear
- Dust reduced for ease of handling and safety of workers
- Available in special, watertight big bags for large scale application.
- Meets the requirements of EN1504-6 for anchoring reinforcement bars.

APPROVALS / STANDARDS

DNV-VALIDATION

DNV Type Approval Certificate number: TAK00000T1
The certification programme for SikaGrout®-9500, which is the basis for issuing the DNV product certificate, comprised the following main activities:

- Validation and acceptance of test methodology, procedures and extent of testing
- Evaluation and acceptance of the external, independent testing laboratory for testing properties of SikaGrout®-9500
- Witnessing and acceptance of the laboratory tests, and the reporting thereof
- Evaluation and witnessing of mock-up tests, and large scale pumping trials, and the acceptance of the reporting thereof
- Audit, evaluation and acceptance of grout manufacturing equipment and facilities
- Audit, evaluation and acceptance of Sika's internal laboratory with respect to production quality control of SikaGrout®-9500

- Evaluation and acceptance of results of the tests and trials carried out to demonstrate the materials suitability for use in offshore applications, such as grouted connections of monopile foundations for offshore wind turbines or similar.
- The validation and certification related to the above mentioned activities are carried out in accordance with applicable EN-standards and DNV-OS-C502 (Offshore concrete structures)

FATIGUE RESISTANCE

- Certified by DNV-OS-C502. More detailed results are available on request.

PRODUCT INFORMATION

Packaging	SikaGrout®-9500 is supplied in special 25 kg and 1000, 1250, 1500 kg wa-tertight big bags.
Shelf Life	12 months from date of production
Storage Conditions	Product must be stored in original, unopened and undamaged sealed pack-aging in dry conditions.
Density	Approximately 2.4 gr/cm ³

TECHNICAL INFORMATION

Compressive Strength	Age	20 °C	10 °C	5 °C	2 °C	(EN 12390-3)
	(N/mm²)					
	1 day	≥ 60	≥ 15			
	2 days	≥ 80	≥ 60	≥ 35	≥ 25	
	3 days	≥ 95	≥ 85	≥ 65	≥ 45	
	7 days	≥ 120	≥ 120	≥ 85	≥ 60	
28 days	≥ 135					
	Results of 75 mm cubes					
	Exposure classes					
	XO, XC4, XD3, XS2, XS3, XF3, XA2, WA					(EN 206)
Modulus of Elasticity in Compression	GPa	20 °C				(EN 13412)
	28 days		49.9			
Tensile Strength in Flexure	N/mm²	20 °C		2 °C		(EN 196-1)
	28 days	≥ 15		≥ 12		
Pull-Out Resistance	≤ 0.6 mm displacement at 75 kN load					(EN 1881)
Shrinkage	Autogenous shrinkage:					(ASTM C1698)
	Age	mm/m				
	after 7 days	- 0.0146				
	after 94 days	- 0.0455				
	after 365 days	+ 0.0006				
Capillary Absorption	≤ 0.05 kg/m ² .h ^{-0.5}					(EN 13057)
Ring Test	no cracking after 180 days					
Splitting tensile strength	Age	20 °C				(EN 12390-6)
	after 28 days	≥ 8 N/mm ²				
	Results of 100 x 200 mm cylinders					

APPLICATION INFORMATION

Mixing Ratio	Approx. 75 lt / 1000 kg powder (min. 70 lt- max. 80 lt)
Consumption	Approximately 2.2 kg powder is needed for 1 litre of mixed mortar. Or, 1000 kg powder will yield approximately 450 to 465 litre of mixed grout.

Layer Thickness	25 - 600 mm
Product Temperature	0 °C min. / +30 °C max. (grouted connection)
Ambient Air Temperature	0 °C min. / +30 °C max. (grouted connection)
Substrate Temperature	0 °C min. / +30 °C max. (grouted connection)
Pot Life	≥ 4 hours
Setting Time	≤ 10 hours

BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

FURTHER DOCUMENTS

- Sika Method Statement: SikaGrout®-9500

ECOLOGY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet (SDS) containing physical, ecological, toxicological and other safety-related data.

APPLICATION INSTRUCTIONS

NOTES ON INSTALLATION

- SikaGrout®-9500 has been especially formulated for use in specific applications. As such SikaGrout®-9500 should be installed by experienced fully trained contractors. Full application procedures are available on request.
- Sands or other products that could affect the products properties must not be added.
- SikaGrout®-9500 which will be exposed to strong drying conditions, e.g. mortar which is directly exposed to heavy wind and/or direct sunlight, should be protected using appropriate curing agents.
- Independent test reports are available on request.

MAINTENANCE

CLEANING

Tools and spillages can be cleaned with water while SikaGrout®-9500 is still uncured. Once hardened, the material can only be removed mechanically.

LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the declared data for this product may vary from country to country. Please consult the local Product Data Sheet for the exact product data.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

Sika Taiwan Ltd.

15F.-1, No. 83, Sec. 1, Nankan Rd.
Luzhu District
Taoyuan City 338207, Taiwan (R.O.C.)
TEL: 03 352 8622 . FAX: 03 352 0470
Info: sika@tw.sika.com
web: twn.sika.com



Product Data Sheet

SikaGrout®-9500
February 2025, Version 03.01
020201000000002072

SikaGrout-9500-en-TW-(02-2025)-3-1.pdf