

## PRODUCT DATA SHEET

# SikaGrout<sup>®</sup>-9800

(formerly MFlow 9800)

High strength grout with applied nanotechnology for grouting offshore wind turbine installations

### DESCRIPTION

SikaGrout<sup>®</sup>-9800 is a shrinkage compensated, cement based grout which when mixed with water, produces a homogeneous, flowable and easy pump able grout with exceptional mechanical and physical properties. Latest best binder packing models and applied cementitious nanotechnology produces a grout with superior technical performance and exceptional rheological properties.

### USES

SikaGrout<sup>®</sup>-9800 has been especially formulated for large scale, pump applications.

- Grouting of grouted connections in offshore installations, e.g. foundations of wind turbines or oil & gas installations.
- Typical applications are pile-sleeve and stab-in-pile grouted connections, clamp repair, leg filling etc...
- Grouting under very harsh conditions, e.g. offshore applications or below water grouting, at temperatures as low as 2°C or up to 42°C.
- All void filling from 30 mm to 600mm thickness where high strength is important.

Contact the Technical Department of your local Sika office regarding any application required not mentioned here.

### CHARACTERISTICS / ADVANTAGES

- C90/105 concrete strength class according EN206 and DIN1045
- Can be installed with a continuous mixing and pumping process. Typical output rates of  $\geq 20 \text{ m}^3/\text{hour}$  per mixing unit.
- Quick return to service and removal of temporary supports due to high early strength build-up.  $\geq 40 \text{ MPa @ 24hrs at } 20^\circ\text{C}$ .
- Very good strength gain at low temperatures.
- No segregation or bleeding to ensure consistent physical performance inside the grouted connection, and to prevent pump blockages.
- Excellent fatigue resistance
- No wash-out during below water grouting.
- Pump able over long distances and large heights.
- Specially graded sands and exceptional flow and low friction increases pump output, reduces installation times and costs as well as reducing pump pressures and wear.
- Available as silo material.

### APPROVALS / STANDARDS

Certified by Det Norske Veritas (DNV)

## PRODUCT INFORMATION

<b>Packaging</b>	SikaGrout®-9800 is supplied by bulk transport and is stored in special job-site silos. Upon request, the material may be available as well in special 1000, 1250 kg kg big bags.
<b>Shelf Life</b>	6 months from date of production
<b>Storage Conditions</b>	Product must be stored in closed silos or warehouse under dry conditions.
<b>Density</b>	Approximately 2.25 gr/cm3 <span style="float: right;">((DIN 18555-2))</span>

## TECHNICAL INFORMATION

<b>Compressive Strength</b>	<b>Determined as part of DNV GL verification:</b>				
	<b>N/mm<sup>2</sup></b>	<b>20 °C</b>	<b>2 °C</b>		(EN 12190-3)
	3 days	83.8	58.9		
	7 days	94.7	79.4		
	28 days	103.1	91.8		
	90 days	124.3	100.5		
	<b>Characteristic compressive strengths (Determined as part of DNV verification):</b>				
	<b>N/mm<sup>2</sup></b>	<b>20 °C</b>	<b>2 °C</b>		(150 x 300 mm cylinders)
	28 days	94.5	88.4		
	<b>Typical values - Additional test results</b>				
	<b>N/mm<sup>2</sup></b>	<b>20 °C</b>	<b>5 °C</b>	<b>2 °C</b>	(EN12390-3)
	3 days	≥ 75	≥ 45	≥ 40	
7 days	≥ 85	≥ 70	≥ 65		
28 days	≥ 95	≥ 80	≥ 75		
<b>Characteristic compressive strengths:</b>					
<b>Specimen size</b>	<b>20 °C</b>	<b>5 °C</b>	<b>2 °C</b>		
100 mm cubes	$X_{k(n)} \geq 90 \text{ N/mm}^2$		$X_{k(n)} \geq 80 \text{ N/mm}^2$		
150 x 300 mm cylinders	$X_{k(n)} \geq 90 \text{ N/mm}^2$				
<b>Exposure classes</b>					
XO, XC4, XD3, XS2, XS3, XF3, XA2, WA				(EN 206-1, DIN 1045-2)	
<b>Modulus of Elasticity in Compression</b>	<b>GPa</b>			(DIN 1048-5)	
	Static	≥ 30			
	Dynamic	≥ 35			
	<b>Determined as part of DNV GL verification:</b>				
		<b>GPa</b>		(EN 12390-13)	
	Static	34.9			
	<b>Poisson ratio (Determined as part of DNV GL verification):</b>				
0.271				(ASTM C469)	
<b>Tensile Strength in Flexure</b>	<b>Age</b>	<b>N/mm<sup>2</sup></b>		(EN12390-5)	
	28 days	≥ 10			
	<b>Characteristic flexural strength:</b>				
	$X_{k(n)} \geq 9 \text{ N/mm}^2$				(700 x 150 x 150 mm bars)
	<b>Determined as part of DNV GL verification:</b>				
	<b>N/mm<sup>2</sup></b>	<b>20 °C</b>	<b>2 °C</b>		
	28 days	13.6	12.7		
<b>N/mm<sup>2</sup></b>	<b>20 °C</b>	<b>2 °C</b>	(EN196-1)		
28 days	13.6	12.7			

<b>Shrinkage</b>	≤ 0.4 mm/m	(Schleibinger shrinkage drain method)
	(test started 90 minutes after mixing – air sealed samples)	
	<b>Shrinkage class:</b> SKVM 0	DAfStb VeBMR Rili)
	<b>Autogenous shrinkage (Determined as part of DNV GL verification):</b> -0.309 mm/m (test started after initial set of the material)	(ASTM C1698)
<b>Bleeding</b>	No bleeding <b>Sedimentation stability:</b> No sedimentation (in accordance of DAfStb Self compacting concrete, section N.1.2.)	

## APPLICATION INFORMATION

<b>Consumption</b>	1000 kg of powder will yield approximately 500 to 525 litre of mixed grout.
<b>Layer Thickness</b>	30 - 600 mm
<b>Product Temperature</b>	+2 °C min. / +42 °C max.
<b>Ambient Air Temperature</b>	+2 °C min. / +42 °C max.
<b>Mixing Ratio</b>	Approximately 145 lt / 1000 kg powder
<b>Substrate Temperature</b>	+2 °C min. / +42 °C max.
<b>Pot Life</b>	≥ 120 minutes
<b>Setting Time</b>	≤ 10 hours

## BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

## FURTHER DOCUMENTS

Sika Method Statement: SikaGrout®-9800

## ECOLOGY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet (SDS) containing physical, ecological, toxicological and other safety-related data.

## APPLICATION INSTRUCTIONS

### NOTES ON INSTALLATION

- Sands or other products that could affect the products properties must not be added.
- SikaGrout®-9800 which will be exposed to strong drying conditions, e.g. mortar which is directly exposed to heavy wind and/or direct sunlight, should be protected using appropriate curing agents.

### EQUIPMENT

Mixer	Jet mixer
(other mixer types need approval from Sika)	
<b>Defined by DNV GL:</b>	
Minimum diameter of grout lines	≥ 2 inch
Grout annulus	30 ≤ t ≤ 600
Pumping length through 2" flexible hose	L ≤ 200 m
Pumping elevated head with 2" flexible hose	H ≤ 20 m

### CLEANING OF TOOLS

Tools and spillages can be cleaned with water while SikaGrout®-9800 is still uncured. Once hardened, the material can only be removed mechanically.

## LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the declared data for this product may vary from country to country. Please consult the local Product Data Sheet for the exact product data.

## LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

### Sika Taiwan Ltd.

15F.-1, No. 83, Sec. 1, Nankan Rd.  
Luzhu District  
Taoyuan City 338207, Taiwan (R.O.C.)  
TEL: 03 352 8622 . FAX: 03 352 0470  
Info: sika@tw.sika.com  
web: twn.sika.com



### Product Data Sheet

SikaGrout®-9800

November 2024, Version 02.01  
02020100000002078

SikaGrout-9800-en-TW-(11-2024)-2-1.pdf