

PRODUCT DATA SHEET

SikaCeram[®]-500 Ceralastic

CEMENTITIOUS 2 IN 1 WATERPROOFING AND TILE ADHESIVE MORTAR

DESCRIPTION

SikaCeram[®]-500 Ceralastic is a cementitious, 1 component, polymer modified, highly deformable, alkali-resistant, synthetic fibre-reinforced tile adhesive with waterproofing and concrete protection mortar properties. Layer thickness < 5,0 mm. Indoor and outdoor use. Classifications: EN 12004: C2 E S2. EN 14891: CM02P. EN 1504-2: PI-MC-IR. Product can also be used for spot-fixing indoor insulating panels.

USES

Tile adhesive for:

- All kinds of ceramic tiles including grès porcelain in large sizes
- Marble and other natural stones
- Laying tiles on floors with underfloor heating
- Indoor over-tiling of existing tiles
- High performance and demanding applications, such as: Swimming pools, façades, balconies and terraces
- Spot-fixing insulating panels

Waterproofing mortar before application of tile adhesive and tiles:

- Swimming pools, terraces, balconies, bathrooms, showers, before the application of ceramic tiles laid with tile adhesives

Concrete protection mortar for:

- Water containment structures and against de-icing salt (chlorides), carbon dioxide deterioration

CHARACTERISTICS / ADVANTAGES

- Tile adhesive, waterproofing and concrete protection mortar, in a single product
- 1 component
- Bonding floor and wall tiles
- Applied by: trowel, brush, roller or spray
- Good adhesion on all types of substrates: cementitious, ceramic tiles, stone, brick, wood and more
- Highly deformable
- Extended open time
- Good crack-bridging ability
- Joint grouting after 12–24 hours
- Single spread bonding
- Spot-fixing insulating panels made of polystyrene, polyurethane foam and glass / rock wool
- Low material consumption compared to traditional systems

APPROVALS / STANDARDS

Tile adhesive

- CE Marking and Declaration of Performance to EN 12004 – Adhesives for Tiles

Waterproofing

- CE Marking and Declaration of Performance to EN 14891 – Liquid applied water impermeable products for use beneath ceramic tiling bonded with adhesives

Concrete protection

- CE Marking and Declaration of Performance to EN 1504-2 - Surface protection product for concrete - Coating

PRODUCT INFORMATION

Chemical Base	Cement, selected aggregates, water retention additives, re-dispersible polymer, fibres	
Packaging	20 kg bags	
Appearance / Colour	Grey powder	
Shelf Life	9 months from date of production	
Storage Conditions	Product must be stored in original, unopened and undamaged sealed packaging in dry conditions at temperatures between +5 °C and +35 °C. Always refer to packaging.	
Maximum Grain Size	D _{max} : 0,315 mm	
Product Declaration	EN 12004	C2 E S2
	EN 14891	CM O2P
	EN 1504-2	IP-MC-IR

TECHNICAL INFORMATION

Permeability to Carbon Dioxide	S _D ≥ 50 m	(EN 1062-6)																					
Permeability to Water Vapour	S _D < 5 m (Class I)	(EN ISO 7783:2012)																					
Capillary Absorption	< 0,1 kg/(m ² h ^{0,5})	(EN 1062-3)																					
Freeze Thaw De-icing Salt Resistance	> 0,8 N/mm ²	(EN 13687-1)																					
Watertightness	No passage (7 days at 1.5 bar)	(EN 14891 - A.7)																					
Crack Bridging Ability	<table border="1"> <tr> <td>Conditions</td> <td>Crack Bridging</td> <td>(EN 1062-7)</td> </tr> <tr> <td>Static</td> <td>> 0,5 mm (Class A3)</td> <td>(EN 1504-2)</td> </tr> <tr> <td>Dynamic, 1000 cycles</td> <td>No cracks (Class B2)</td> <td></td> </tr> <tr> <td>Conditions</td> <td>Crack Bridging</td> <td>(EN 14891)</td> </tr> <tr> <td>Standard (+23 °C)</td> <td>≥ 0,75 mm</td> <td></td> </tr> <tr> <td>Low temperature (- 5 °C)</td> <td>≥ 0,75 mm</td> <td></td> </tr> <tr> <td>Low temperature (-20 °C)</td> <td>≥ 0,75 mm *</td> <td></td> </tr> </table>	Conditions	Crack Bridging	(EN 1062-7)	Static	> 0,5 mm (Class A3)	(EN 1504-2)	Dynamic, 1000 cycles	No cracks (Class B2)		Conditions	Crack Bridging	(EN 14891)	Standard (+23 °C)	≥ 0,75 mm		Low temperature (- 5 °C)	≥ 0,75 mm		Low temperature (-20 °C)	≥ 0,75 mm *		
Conditions	Crack Bridging	(EN 1062-7)																					
Static	> 0,5 mm (Class A3)	(EN 1504-2)																					
Dynamic, 1000 cycles	No cracks (Class B2)																						
Conditions	Crack Bridging	(EN 14891)																					
Standard (+23 °C)	≥ 0,75 mm																						
Low temperature (- 5 °C)	≥ 0,75 mm																						
Low temperature (-20 °C)	≥ 0,75 mm *																						
	* With reinforcing mesh																						
Tensile Adhesion Strength	<table border="1"> <tr> <td>Initial</td> <td>≥ 1,5 N/mm²</td> <td>(EN 14891)</td> </tr> <tr> <td>Water immersion</td> <td>≥ 1,0 N/mm²</td> <td></td> </tr> <tr> <td>Heat ageing</td> <td>≥ 1,0 N/mm²</td> <td></td> </tr> <tr> <td>Freeze-thaw cycles</td> <td>≥ 1,0 N/mm²</td> <td></td> </tr> <tr> <td>Lime water immersion</td> <td>≥ 1,0 N/mm²</td> <td></td> </tr> <tr> <td>Chlorinated water immersion</td> <td>≥ 0,5 N/mm²</td> <td></td> </tr> </table>	Initial	≥ 1,5 N/mm ²	(EN 14891)	Water immersion	≥ 1,0 N/mm ²		Heat ageing	≥ 1,0 N/mm ²		Freeze-thaw cycles	≥ 1,0 N/mm ²		Lime water immersion	≥ 1,0 N/mm ²		Chlorinated water immersion	≥ 0,5 N/mm ²					
Initial	≥ 1,5 N/mm ²	(EN 14891)																					
Water immersion	≥ 1,0 N/mm ²																						
Heat ageing	≥ 1,0 N/mm ²																						
Freeze-thaw cycles	≥ 1,0 N/mm ²																						
Lime water immersion	≥ 1,0 N/mm ²																						
Chlorinated water immersion	≥ 0,5 N/mm ²																						
Transverse deformation	≥ 10 mm	(EN 12002)																					

SYSTEM INFORMATION

System Structure	<p>Tile adhesive: For the following substrates, a primer must be used:</p> <table border="1"> <thead> <tr> <th>Substrate</th> <th>Primer</th> </tr> </thead> <tbody> <tr> <td>Gypsum, plaster or anhydrite screed</td> <td>Sika® Primer-11 W</td> </tr> <tr> <td>Existing ceramic tiles, PVC sheet, linoleum and existing vinyl tiled floors</td> <td>Sika® Primer-21 W</td> </tr> <tr> <td>Tile Adhesive</td> <td>SikaCeram®-500 Ceralastic</td> </tr> </tbody> </table> <p>Waterproofing layer:</p> <table border="1"> <tbody> <tr> <td>Waterproofing tapes (control joints and small movement)</td> <td>Sika® SealTape B Sika® SealTape F Sika® SealTape S</td> </tr> <tr> <td>Waterproofing strip (Large movement)</td> <td>Sikadur-Combiflex® SG system</td> </tr> <tr> <td>Waterproofing mortar</td> <td>SikaCeram®-500 Ceralastic</td> </tr> </tbody> </table>			Substrate	Primer	Gypsum, plaster or anhydrite screed	Sika® Primer-11 W	Existing ceramic tiles, PVC sheet, linoleum and existing vinyl tiled floors	Sika® Primer-21 W	Tile Adhesive	SikaCeram®-500 Ceralastic	Waterproofing tapes (control joints and small movement)	Sika® SealTape B Sika® SealTape F Sika® SealTape S	Waterproofing strip (Large movement)	Sikadur-Combiflex® SG system	Waterproofing mortar	SikaCeram®-500 Ceralastic
Substrate	Primer																
Gypsum, plaster or anhydrite screed	Sika® Primer-11 W																
Existing ceramic tiles, PVC sheet, linoleum and existing vinyl tiled floors	Sika® Primer-21 W																
Tile Adhesive	SikaCeram®-500 Ceralastic																
Waterproofing tapes (control joints and small movement)	Sika® SealTape B Sika® SealTape F Sika® SealTape S																
Waterproofing strip (Large movement)	Sikadur-Combiflex® SG system																
Waterproofing mortar	SikaCeram®-500 Ceralastic																

APPLICATION INFORMATION

Mixing Ratio	Floor application	~4,8 litres per 20 kg bag	(24 % ± 1 %)												
	Wall application	~4,0 litres per 20 kg bag	(20 % ± 1 %)												
Fresh Mortar Density	~1,6 kg/l														
Consumption	<p>Tile adhesive Consumption is dependent on the substrate, surface profile, roughness and application technique. As a guide for a single adhesive layer:</p> <table border="1"> <thead> <tr> <th>Size of tiles</th> <th>Notched trowel size</th> <th>Size of tiles</th> </tr> </thead> <tbody> <tr> <td>Small</td> <td>8 mm square notch</td> <td>~ 2,5 kg/m²</td> </tr> <tr> <td>Medium</td> <td>10 mm square notch</td> <td>~ 3 kg/m²</td> </tr> <tr> <td>Large</td> <td>15 mm half-moon</td> <td>~ 6,5 kg/m²</td> </tr> </tbody> </table> <p>Waterproofing and Concrete protection ~1,2 kg/m² per mm of thickness. These figures are theoretical and do not allow for any additional material due to surface porosity, surface profile, variations in level or wastage etc.</p>			Size of tiles	Notched trowel size	Size of tiles	Small	8 mm square notch	~ 2,5 kg/m ²	Medium	10 mm square notch	~ 3 kg/m ²	Large	15 mm half-moon	~ 6,5 kg/m ²
Size of tiles	Notched trowel size	Size of tiles													
Small	8 mm square notch	~ 2,5 kg/m ²													
Medium	10 mm square notch	~ 3 kg/m ²													
Large	15 mm half-moon	~ 6,5 kg/m ²													
Layer Thickness	5,0 mm max.														
Ambient Air Temperature	+5 °C min. / +30 °C max.														
Substrate Temperature	+5 °C min. / +30 °C max.														
Maturing Time	~3 min														
Pot Life	~40 min at 23 °C														
Open Time	≥ 0,5 N/mm ² after 30 min		(EN 1346)												
Curing Time	3 hours depending on ambient conditions														

Curing Treatment

Protect from adverse weather conditions, such as extremely high or freezing temperatures, rain, direct exposure to sun, for at least 12–24 hours from application.

Applied Product Ready for Use

Use	Waiting time
Walkability	12 hours
Grouting - floors	24 hours
Grouting - walls	3 hours
Full traffic	48 hours
Water immersion	72 hours

APPLICATION INSTRUCTIONS

SUBSTRATE QUALITY / PRE-TREATMENT

Tile adhesive, waterproofing and concrete protection mortar

Cementitious substrates must be sufficiently cured and dried (2–6 weeks), All substrates must be structurally sound, able to support the weight of the new tiling and provide a stable and securely fixed background. Surfaces shall be clean, dry, free of any loose or friable particles, contaminants such as dust, dirt, oil, wax, polish grease, cement laitance or efflorescence.

Depending on the substrate condition and contaminants to be removed from the surface, use adequate preparation techniques to remove all traces of any materials that could reduce the product's adhesion to the substrate. Smooth surfaces should be roughened lightly to improve adhesion. To confirm adequate surface preparation and adhesion, carry out a small trial before full application.

Any small surface defects and variations in level, profile, or around exposed aggregates can be prefilled and levelled with an additional layer of SikaCeram®-500 Ceralastic to a maximum thickness of 5 mm, applied at least 24 hours before full adhesive application. For larger and thicker areas of surface re-profiling and making good, use appropriate mortars from the Sika MonoTop® or Sikafloor® Level range. Cracks in substrates must be identified and sealed appropriately e.g. with Sikadur® epoxy resins.

For applications in hot climates / environments, or on absorbent substrates, thoroughly pre-dampen the surface immediately prior to product application. Avoid any ponding / standing water on the surface. Surface must not be damp to touch.

Tile adhesive

When laying tiles on non-absorbent or substrates with limited absorbency, such as existing ceramic tiles, painted surfaces etc. Check to confirm these surfaces are all stable, firmly and securely bonded. Then use suitable degreasing/descaling products to thoroughly and completely clean the surface.

For tiling in constantly damp or wet rooms, then a suitable Sika® waterproofing product / systems should be applied to the substrate before tiling.

MIXING

Pour the recommended amount of clean cold water into a suitable, clean mixing container.

While stirring, slowly add SikaCeram®-500 Ceralastic powder to the water and then mix thoroughly using a low speed (~500 rpm) electric drill mixer until the material is fully mixed and lump free. Avoid entraining air into the mix by over mixing.

Allow the mixed product to 'mature' for 2–3 minutes before remixing for 30 seconds.

The finished mix should have a creamy consistency, uniformly coloured and it is easy to apply and spread.

APPLICATION

Tile Adhesive

SikaCeram®-500 Ceralastic is applied using a suitable notched trowel.

Apply sufficient adhesive to the prepared fixing surface with the appropriate trowel and comb to the required bed thickness. Apply sufficient product to ensure adequate 'wetting' of the backs of the tiles.

Tiling must be carried out on freshly applied adhesive, exerting adequate pressure to ensure 100 % complete and uniform contact with the adhesive to achieve optimum adhesion. Tiling must be carried out on freshly applied adhesive, exerting adequate pressure to ensure complete and uniform contact with the adhesive and thus optimum bond.

If a skin forms on the surface of the adhesive, immediately remove the adhesive layer with the trowel, discard material and apply a fresh layer of SikaCeram®-500 Ceralastic adhesive.

Adjust tiles if required.

Clean off surplus adhesive from tile face and between tile joints before the adhesive has dried.

After the required waiting time apply the appropriate grout into the tile joints

Refer to the individual Product Data Sheets.

Waterproofing and tiling in two steps

Waterproofing tapes must always be applied over control joints subject to small movements and other critical areas such as corners, edges and joints between different substrate materials:

Apply Sika® SealTape B self-adhering tape onto prepared substrate.

Apply Sika® SealTape S or Sika® SealTape F onto a

Product Data Sheet

SikaCeram®-500 Ceralastic
October 2019, Version 01.01
020404020010000322

fresh layer of SikaCeram®-500 Ceralastic and cover with a second layer of SikaCeram®-500 Ceralastic. Refer to the individual Product Data Sheets. After sealing tapes have been laid, wet the substrate. Apply SikaCeram®-500 Ceralastic with a flat trowel, pressing the mortar onto the substrate in order to ensure proper adhesion. The total thickness of application should be at least 3 mm in 2 layers of 2 mm maximum to achieve a consistent and defect free continuous layer. Waiting time between two layers is ~3 hours. After ~4 hours apply SikaCeram®-500 Ceralastic as a tile adhesive.

Waterproofing and bonding of tiles in one step with special trowel*

- On floors, SikaCeram®-500 Ceralastic can be applied in one step using the special 'Ceralastic trowel'.
- The choice of SikaCeram®-500 Ceralastic 'Ceralastic trowel' depends on the tile size to ensure a complete covering of the product on the underside of tile. A 10 mm 'Ceralastic trowel' is recommended for tile sizes up to 25x25 cm; for larger tile sizes use a 15 mm half moon trowel.
- The adjustable steel pins must exceed the trowel tooth length by at least 3 mm. The resulting waterproofing layer below the tile adhesive layer should be a minimum of 2 mm.
- Wet the substrate and apply SikaCeram®-500 Ceralastic with the 'Ceralastic trowel' then lay the tile directly onto the wet mortar.
- Apply sufficient product to ensure complete 'wetting' of the back of the tiles.
- Total thickness must be between 4 and 5 mm in a consistent and continuous layer.

* Not suitable for swimming pools and vertical application

CLEANING OF TOOLS

Clean all tools and application equipment with water after use. Hardened material can only be removed mechanically.

LIMITATIONS

- Gypsum plaster and anhydrite screed substrates must have a maximum moisture content of 0,5 %.
- For swimming pools and vertical applications use SikaCeram®-500 Ceralastic in two application steps. The product must always be covered with tiles.
- Do not apply the waterproofing mortar and tile adhesive in one step for vertical applications.

Sika Taiwan Ltd.

No. 1380, Sec. 3, Fu-Kwo Rd., Luchu Dist.
33849 Taoyuan City, Taiwan, R.O.C.
TEL: 03 352 8622 . FAX: 03 352 0470
sika@tw.sika.com . tw.sika.com

- Refer to tile manufacturers instructions for guidance on providing expansion joints
- If service temperatures below -20 °C are expected, reinforce SikaCeram®-500 Ceralastic with an alkali-resistant glass fibre mesh.
- Do not use on marble or natural stone tiles if they are sensitive to water.

BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the declared data for this product may vary from country to country. Please consult the local Product Data Sheet for the exact product data.

ECOLOGY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet (SDS) containing physical, ecological, toxicological and other safety-related data.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

SikaCeram-500Ceralastic-en-TW-(10-2019)-1-1.pdf