

# PRODUCT DATA SHEET

## Sika® CorroTop Neu WEA

SOLVENT-CONTAINING, 1-PACK COATING BASED ON SYNTHETIC RESIN FOR STEEL AND PRIMER COATED ZINC

### DESCRIPTION

Easy applicable coating with a smooth, glossy surface.

### USES

Sika® CorroTop Neu WEA may only be used by experienced professionals.

Corrosion protection and colour design for steel or primer coated galvanized steel constructions, e.g. warehouse structures, machine parts, wall and ceiling cladding, doors, railings, for indoor and outdoor.

### CHARACTERISTICS / ADVANTAGES

- Quick-drying
- Stackable
- Excellent adhesion on old coatings, primed galvanized surfaces and aluminium

### PRODUCT INFORMATION

<b>Packaging</b>	Sika® CorroTop Neu WEA	1 kg net.
	Sika® Thinner S	3 l
<b>Appearance / Colour</b>	RAL 7035, RAL 7038 Green colour shades of ENERCON EC-A, EC-B, EC-C, EC-D and EC-E. Slight colour deviations are possible due to raw material characteristics.	
<b>Shelf Life</b>	2 years	
<b>Storage Conditions</b>	In originally sealed containers in a cool and dry environment.	
<b>Density</b>	~1.3 kg/l	
<b>Solid Content</b>	~56 % by volume ~73 % by weight	

### TECHNICAL INFORMATION

<b>Chemical Resistance</b>	Resistant to weathering.
<b>Thermal Resistance</b>	Dry heat up to max. + 100°C

## SYSTEM INFORMATION

### Systems

Manual derusting steel:  
2 x SikaCor® Aktivprimer Rapid WEA  
1 x Sika® CorroTop Neu WEA

Maintenance on old coatings:  
1 - 2 x Sika® CorroTop Neu WEA

The product is not suitable for underwater exposure, resp. permanent condensation. When applying light and brilliant colours of Sika® CorroTop Neu WEA a 2<sup>nd</sup> coat may become necessary to achieve perfect opacity.

## APPLICATION INFORMATION

### Thinner

If necessary max. 3 % Sika® Thinner B may be added to adapt the viscosity.

### Consumption

Theoretical material-consumption/VOC without loss for medium dry film thickness:

Dry film thickness	60 µm *
Wet film thickness	110 µm
Consumption	~0.140 kg/m <sup>2</sup>
VOC	~36.5 g/m <sup>2</sup>

\* Max. dry film thickness: 120 µm

### Product Temperature

Min. + 5 °C

### Relative Air Humidity

Max. 85 %, except the surface temperature is significantly higher than the dew point temperature, it shall be at least 3 K above dew point.

### Surface Temperature

Min. + 5 °C

### Drying Stage 6

	<b>Dry film thickness 60 µm</b>	(ISO 9117-5)
+ 5°C after	21 h	
+ 23°C after	10 h	

### Waiting Time / Overcoating

At + 20°C Min. 12 h

### Drying Time

#### Final drying time

Depending on layer thickness and temperature final hardness is usually achieved within several days.

## APPLICATION INSTRUCTIONS

### SURFACE PREPARATION

#### Steel:

Surface must be free from oil, grease, dirt, as well as free of scale and mill scale.

Blast-cleaning to Sa 2 ½ according to ISO 12944-4 will give the best result. In case of lower exposure as e.g. in rural atmosphere or indoors, manual surface preparation (power tool cleaning) to St 2 may be sufficient.

#### Old coatings:

Well adhering coatings need only to be cleaned.

Loose particles must be removed, corroded areas must be derusted to PSa 2½, PMa or PSt 2 and patched up with Sika® CorroTop Neu WEA or SikaCor® Aktivprimer Rapid WEA.

For contaminated and weathered surfaces e.g. galvanized or primed areas we recommend to clean with SikaCor® Wash.

### MIXING

Sika® CorroTop Neu WEA is supplied ready for use. Stir thoroughly prior to application.

### APPLICATION

The method of application has a major effect on achieving uniform thickness and appearance. Adding solvents reduces the sag resistance and the dry film thickness. In case of application by roller or brush, additional applications may become necessary to achieve the required coating thickness, depending on type of construction, site conditions, colour shade etc. Prior to major coating operations a test application on site may be useful to ensure the selected application method will provide the requested results.

#### By brush and roller

### CLEANING OF TOOLS

Sika® Thinner B

## BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

## LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the declared data for this product may vary from country to country. Please consult the local Product Data Sheet for the exact product data.

## ECOLOGY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet (SDS) containing physical, ecological, toxicological and other safety-related data.

### DIRECTIVE 2004/42/CE - LIMITATION OF EMISSIONS OF VOC

According to the EU Directive 2004/42/CE, the maximum allowed content of VOC (product category IIA / i type Sb) is 500 g/l (Limits 2010) for the ready to use product.

The maximum content of Sika® CorroTop Neu WEA is < 500 g/l VOC for the ready to use product.

## LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

### Sika Taiwan Ltd.

No. 1380, Sec. 3, Fu-Kwo Rd., Luchu Dist.  
33849 Taoyuan City, Taiwan, R.O.C.  
TEL: 03 352 8622 . FAX: 03 352 0470  
sika@tw.sika.com . tw.sika.com

SikaCorroTopNeuWEA-en-TW-(08-2019)-2-1.pdf

Product Data Sheet  
Sika® CorroTop Neu WEA  
August 2019, Version 02.01  
020601000060000015

